

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 741 333 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

06.11.1996 Bulletin 1996/45

(51) Int. Cl.⁶: **G03F 7/029**, G03F 3/10

(21) Application number: **96201158.1**

(22) Date of filing: **27.04.1996**

(84) Designated Contracting States:
DE FR GB IT NL

(30) Priority: **05.05.1995 US 435560**

(71) Applicant: **Bayer Corporation**
Pittsburgh, PA 15219-2502 (US)

(72) Inventor: **Wilczak, Wojciech A.**
Jersey City, New Jersey 07302 (US)

(74) Representative: **Ramon, Charles Lucien et al**
Agfa-Gevaert N.V.
Dienst Intellectuele Eigendom 3800
Septestraat 27
2640 Mortsel (BE)

(54) Photopolymerizable compositions

(57) The present invention relates a photopolymerizable composition which comprises:

- A) one or more ethylenically unsaturated, free-radical polymerizable monomers;
- B) one or more organic binders; and
- C) one or more photoinitiators, wherein the photoinitiator is an acyl or diacyl phosphine oxide, in combination with a fluorescent optical brightener;

and a process for producing such a photopolymerizable composition.

EP 0 741 333 A1

Description

Field of the Invention

5 The present invention relates to improved photopolymerizable compositions useful in color proofing films and printing plates capable of producing images upon treatment with actinic radiation.

Background of the Invention

10 In the graphic arts, it is desirable to produce a three or more color proof to assist in correcting a set of color separation films prior to using them to produce printing plates. The proof should reproduce the color quality that will be obtained during the printing process. The proof must be a consistent duplicate of the desired halftone image. Visual examination of a color proof should show the color rendition to be expected from press printing using the color separations and any defects on the separations which might need to be altered before making the printing plates, which are
15 then utilized to finally reproduce the color image.

Photopolymerizing and photocrosslinking compounds have widespread applications in the industry. For example, processes related to coatings, photoresists, lithographic plates and the like are based on such compounds. Photopolymerization and photocrosslinking have been subject of several review articles such as, for example, in Encyclopedia of Polymer Science and Engineering, Volume 4, page 350 (John Wiley & Sons, Inc., New York, 1986) and ibid., Vol. 11, 187 (1988). Generally, photoreactive compositions contain monomers which, under the action of light, polymerize (photopolymerization) or crosslink when additional monomers are present (photocrosslinking). They may also crosslink on their own if they are multifunctional. A photoinitiator (or photosensitizer) is generally used in such reactions, although it is not always necessary.

Photopolymerizable mixtures comprising a polymerizable monomer, a binder and a photoinitiator are well known in the prior art. Such compositions are described in general in U.S. Patents 3,782,961; 3,850,770; 3,960,572; 4,019,972; and 4,250,248. German Patent DOS 2,040,390 and French Patent 1,520,856 describe the use of aromatic ketones such as benzil ketals, benzoin ethers, and alpha-methylol derivatives of benzoin ethers. For these compositions very long exposure times are normally necessary because of lower than acceptable photosensitivity.

Photopolymerizable monomers are also known in the art which contain certain combinations of photoinitiators and activators to increase photosensitivity. Among these are, for example, combinations of carbonyl group-containing initiators and tertiary amines. Such mixtures displaying a synergistic effect are described in U.S. Patents 4,054,682; 4,071,424; and 3,759,807. A disadvantage of these mixtures is that they have a relatively short shelf life because the amines can easily bleed out, in particular from a coating.

U.S. Patent 4,292,152 describes the use of acyl phosphine oxide initiators to improve the photosensitivity of polymerizable compositions. These compositions are faster (more photosensitive) than the other prior art compositions. However, they are still not sufficiently photosensitive to substantially reduce the irradiation time in today's UV curing and imaging industry.

Fluorescent brighteners have been used as additives in some photohardenable materials to alleviate undesirable yellowing of the film, as taught in U.S. Patents 3,644,394; 2,784,183; and 2,563,493. Fluorescent brighteners have also
40 been shown to reduce halation effects in photohardenable compositions, as described in U.S. Patent 3,854,950.

U.S. Patent 5,300,399 teaches a negative-acting color proofing element. The element sequentially comprises a strippable cover sheet which is transparent to actinic radiation; a crosslinked layer containing a polymer having phenolic groups; a color layer, containing a colorant, a polymeric binder, a polymerizable monomer and, optionally, a photoinitiator; a photoadhering layer, containing a linear photosensitive polymer containing ethylenically unsaturated, free-radical polymerizable groups and having a molecular weight greater than 3,000, a polymerizable monomer, and, optionally,
45 a free radical photoinitiator; a thermoplastic adhesive layer; and a receiver sheet, at least one of the color layer and the photoadhering layer containing the photoinitiator.

However, it is sometimes desirable to blanket-expose the finished proof to actinic radiation in order to photoharden the top layer in order to provide blocking-and-scratch resistance. It was found that the photoadhering layer taught in
50 5,300,399 becomes discolored (yellows) when exposed to UV-light.

It is an object of the present invention to provide even more reactive initiators for rapid crosslinking of polymerizable compositions. It is also an object of the present invention to provide photopolymerizable which can be used in a color proofing element or on a printing plate. When utilized in color proofing, the polymerizable composition of the present invention remedies unwanted discoloration when a color proofing element is exposed to UV-light. These objects have
55 been achieved, surprisingly, by incorporating fluorescent brighteners into the photoinitiator composition, along with an acyl or diacyl phosphine oxide. The prior art does not suggest the photosensitivity-enhancing properties of fluorescent brighteners on acyl or diacyl phosphine oxide photoinitiators. The composition and process of the present invention provide a five- to ten-fold increase in the photosensitivity of compositions when compared with the same compositions lacking the fluorescent brightener.

Summary of the Invention

In the present invention, one produces a photopolymerizable composition which comprises:

- 1) one or more ethylenically unsaturated, free-radical polymerizable monomers,
- 2) one or more organic binders; and
- 3) one or more photoinitiators, wherein the photoinitiator is an acyl or diacyl phosphine oxide, in combination with a fluorescent optical brightener.

The present invention also relates to a process for producing a photopolymerizable composition by providing an admixture of:

- 1) one or more ethylenically unsaturated, free-radical polymerizable monomers;
- 2) one or more organic binders; and
- 3) a combination of an acyl or diacyl phosphine oxide and a fluorescent optical brightener.


Detailed Description of the Preferred Embodiment

The ethylenically unsaturated, free radical polymerizable monomers in the photopolymerizable composition of the present invention preferably comprise addition polymerizable, non-gaseous (boiling temperature above 100°C at normal atmospheric pressure), ethylenically-unsaturated organic compounds containing at least one, and preferably at least two, terminal ethylenically unsaturated groups, and being capable of forming a high weight average molecular weight polymer by free radical initiated, chain propagating addition polymerization. The most preferred compounds are acrylate or methacrylate monomers, as are well known in the art. Suitable polymerizable monomers nonexclusively include triethylene glycol dimethacrylate, tripropylene glycol diacrylate, tetraethylene glycol dimethacrylate, diethylene glycol dimethacrylate, 1,4-butanediol diacrylate, 1,6-hexanediol dimethacrylate, pentaerythritol tetraacrylate, trimethylol propane triacrylate, trimethylol propane trimethacrylate, di-pentaerythritol monohydroxypentaacrylate, pentaerythritol triacrylate, bisphenol-A-ethoxylate dimethacrylate, trimethylolpropane ethoxylate triacrylate, trimethylolpropane propoxylate triacrylate, and bisphenol A diepoxide dimethacrylate.


Other useful monomers include the urethane monomers described in copending United States Application Serial No. 221,676 filed on April 1, 1994. These monomers may be prepared by reacting an isocyanate with a partial ester of acrylic acid or methacrylic acid and a polyhydric alcohol. They may also be provided by reacting an acrylate such as dipentaerythritol pentaacrylate with an isocyanate such as 2-heptyl-3,4-bis-(9-isocyanatononyl)-1-pentyl cyclohexane.

Free radical liberating photoinitiators used in the photopolymerizable composition of the present invention are a combination of an acyl or diacyl phosphine oxides and a fluorescent optical brightener. Copending U.S. Application Serial Number _____ (Attorney's Docket DA 3101), filed on the same date as this Application, describes a color proofing element and method for producing such a color proofing element, wherein the color proofing element utilizes the photopolymerizable composition of the present invention, which contains as a photoinitiator an acyl or diacyl phosphine oxide compound, in combination with a fluorescent optical brightener. Surprisingly, this combination, when used in the top layer of a color proofing element, not only does not substantially change color on exposure to actinic light, but also protects the lower layers from harmful radiation.

The acyl and diacyl phosphine oxides which may be utilized in the photoinitiator, respectively, have the following formulas I and II:



Formula I



Formula II

where:

R₁ and R₆ is a branched or unbranched alkyl of 1 to 18 carbon atoms, substituted or unsubstituted cycloalkyl of 5 or 6 carbon atoms, C₆-C₁₈ aryl which is unsubstituted or substituted by C₁-C₁₈ alkyl or C₁-C₁₈ alkoxy, or an S-containing or N-containing five-membered or six-membered heterocyclic radical, R₁ and R₆ being the same or different,

R_2 has the same meaning as R_1 , or is C_1 - C_{18} alkoxy, C_6 - C_{18} aryloxy or aralkoxy (C_6 - C_{18} aryl, C_1 - C_{18} alkyl), R_1 and R_2 being the same or different or together to form a ring, and

R_3 , R_4 and R_5 are a tertiary alkyl of 4 to 18 carbon atoms, or a tertiary cycloalkyl of 5 or 6 carbon atoms, or is a C_6 - C_{18} cycloalkyl, C_6 - C_{18} aryl, or 5-membered or 6-membered heterocyclic radical containing S, N or O as heteroatoms which contain substituents A and B bonded at least to the two ring carbon atoms, capable of substitution, which are adjacent to the point of attachment to the carbonyl group of the R_3 group, A and B being identical or different, and each being C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy, C_1 - C_{18} alkyl, C_1 - C_{18} alkylthio, C_6 - C_{18} cycloalkyl, C_6 - C_{18} aryl or halogen. R_3 , R_4 and R_5 can be the same or different.

Fluorescent optical brighteners which may be utilized in the photopolymerizable composition of the present invention include those described in United States Patents 2,784,183 and 3,644,394. Particularly preferred are 2,2'-(thiophenediyl)-bis-(t-butyl benzoxazole); 2-(stibyl-4'')-(naphtho-1',2',4,5)-1,2,3-triazole-2''-sulfonic acid phenyl ester; and 7-(4'-chloro-6''-diethylamino-1',3',5'-triazine-4'-yl)amino-3-phenyl coumarin. Fluorescent optical brighteners whose building blocks include one or more of: stilbene, triazine, thiazole, benzoxazole, coumarin, xanthene, triazole, oxazole, thiophene or pyrazoline may be utilized in the photopolymerizable composition of the present invention.

Suitable binder resins are those well known in the art and may include styrene/maleic anhydride copolymers and their half esters; acrylic polymers and copolymers; polyamides; polyvinyl pyrrolidones; cellulosic resins; phenolic resins; polyvinyl acetals; polyvinyl acetates and their copolymers; and mixtures thereof.

In the practice of the present invention, the one or more ethylenically unsaturated, free radical polymerizable monomers are preferably present in the photopolymerizable composition in an amount ranging from about 5 to 70% based on the weight of the solids in the composition. A preferred range is from about 10 to 60%, more preferably from about 20 to 50%.

In the practice of the present invention, the one or more organic binders are preferably present in the photopolymerizable composition in an amount sufficient to bind the components in a uniform mixture and to provide a uniform film, ranging from about 20 to 80% based on the weight of the solids in the composition. A preferred range is from about 30 to 75%, more preferably from about 40 to 70%.

In the practice of the present invention, the one or more photoinitiators are preferably present in the photopolymerizable composition in an amount ranging from about 1 to 30% based on the weight of solids in the composition. A preferred range is from about 3 to 20%, more preferably from about 5 to 15%.

The following nonlimiting examples serve to illustrate the present invention.

Comparative Example 1

The following photosensitive solution was prepared:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset[®] 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer[®] 399 available from Sartomer Co.) - 5 grams;
3. 2,4,6-trimethylbenzoyl-diphenylphosphine oxide (Lucirin[®] TPO available from BASF) - 1 gram;
4. Methyl Ethyl Ketone - 89 grams.

This solution was coated on 3 mil thick clear polyester sheet (Melinex[®] 505 available from ICI) with a Meyer[®] rod #12, and dried in an oven for 2 minutes to give a clear film. This film was exposed through an UGRA target for 1 minute in a Theimer[®] unit equipped with a 5 kW lamp, and developed with a CPD (Enco Division of Hoechst Celanese Corporation) Color Proofing developer. The number of photohardened solid steps on the Stouffer stepwedge indicated functional photospeed. Four (4) solid steps were obtained.

Example 1

The procedure of Comparative Example 1 was repeated, except 1 gram of a fluorescent brightener (Uvitex[®] OB available from Ciba) was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset[®] 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer[®] 399 available from Sartomer Co.) - 5 grams;
3. 2,4,6-trimethylbenzoyl-diphenylphosphine oxide (Lucirin[®] TPO available from BASF) - 1 gram;
4. 2,2'-(2,5-thiophenediyl)bis(t-butylbenzoxazole) (Uvitex[®] OB available from Ciba) - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

The procedure was repeated as in Comparative Example 1. The film after development gave solid step 10.

Example 2

Example 1 was repeated, except the Uvitex® OB was replaced with an equal amount of fluorescent brightener Hakkol® PY-1800 (available from Hakkol Chemical Co., Japan), 7-(4'-chloro-6'-diethylamino-1'-3'-5'-triazine-4'-yl)amino-3-phenyl coumarin, which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. 2,4,6-trimethylbenzoyl-diphenylphosphine oxide (Lucirin® TPO available from BASF) - 1 gram;
4. 7-(4'-chloro-6'-diethylamino-1'-3'-5'-triazine-4'-yl)amino-3-phenyl coumarin (Hakkol® PY-1800) - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

After development, solid step 9 was obtained.

Example 3

Example 2 was repeated, except the Hakkol® PY - 1800 was replaced with an equal amount of a fluorescent brightener 7-diethylamino-4-methylcoumarin, which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. 2,4,6-trimethylbenzoyl-diphenylphosphine oxide (Lucirin® TPO available from BASF) - 1 gram;
4. 7-diethylamino-4-methylcoumarin - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

Solid step 11 was obtained.

Example 4

Example 3 was repeated, except 7-diethylamino-4-methylcoumarin was replaced with an equal amount of Eastobrite® OB-1 Fluorescent Brightener (available from Eastman Chemical Company), 2,2'-(1,2-Ethanediyl-di-4,1-phenylene)bisbenzoxazole, which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. 2,4,6-trimethylbenzoyl-diphenylphosphine oxide (Lucirin® TPO available from BASF) - 1 gram;
4. 2,2'-(1,2-Ethanediyl-di-4,1-phenylene)bisbenzoxazole, Eastobrite® OB-1 Fluorescent Brightener (available from Eastman Chemical Company) - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

A solid step 11 was obtained.

Comparative Example 2

Comparative Example 1 was repeated, except the 2,4,6-trimethylbenzoyl-diphenylphosphine oxide (Lucirin® TPO available from BASF) was replaced with an equal amount of bis (2,6-dimethoxybenzoyl)-2,4,4-trimethyl pentyl phosphine oxide (CGI® 403 available from Ciba Corporation), which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. Bis (2,6-dimethoxybenzoyl)-2,4,4-trimethyl pentyl phosphine oxide (CGI® 403 available from Ciba Corporation) - 1 gram;
4. Methyl Ethyl Ketone - 89 grams.

After exposure and development the material gave solid step 5.

Example 5

Comparative Example 2 was repeated, except 1 gram of a fluorescent brightener (Uvitex® OB available from Ciba) was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. Bis (2,6-dimethoxybenzoyl)-2,4,4-trimethyl pentyl phosphine oxide (CGI® 403 available from Ciba Corporation - 1 gram;
4. 2,2'-(2,5-thiophenediyl)bis(t-butylbenzoxazole) (Uvitex® OB available from Ciba) - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

After exposure and development the material gave solid step 10.

Example 6

Example 5 was repeated, except Uvitex® OB was replaced with an equal amount of fluorescent brightener Hakkol® PY-1800 (available from Hakkol Chemical Co., Japan), 7-(4'-chloro-6'-diethylamino-1'-3'-5'-triazine-4'-yl)amino-3-phenyl coumarin, which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. Bis (2,6-dimethoxybenzoyl)-2,4,4-trimethyl pentyl phosphine oxide (CGI® 403 available from Ciba Corporation - 1 gram;
4. 7-(4'-chloro-6'-diethylamino-1'-3'-5'-triazine-4'-yl)amino-3-phenyl coumarin - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

After exposure and development the material gave solid step 11.

Example 7

Example 6 was repeated; except Hakkol® PY-1800 was replaced with an equal amount of a fluorescent brightener 7-diethylamino-4-methylcoumarin, which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. Bis (2,6-dimethoxybenzoyl)-2,4,4-trimethyl pentyl phosphine oxide (CGI® 403 available from Ciba Corporation - 1 gram;
4. 7-diethylamino-4-methylcoumarin - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

After exposure and development the material gave a solid step 12.

Example 8

Example 7 was repeated, except 7-diethylamino-4-methylcoumarin was replaced with an equal amount of Eastobrite® OB-1 Fluorescent Brightener (available from Eastman Chemical Company), 2,2'-(1,2-Ethanediyldi-4,1-phenylene)bisbenzoxazole, which was added to the solution:

1. Styrene/maleic anhydride half ester copolymer resin (Scriptset® 540 available from Monsanto) - 5 grams;
2. Dipentaerythritol pentaacrylate (Sartomer® 399 available from Sartomer Co.) - 5 grams;
3. Bis (2,6-dimethoxybenzoyl)-2,4,4-trimethyl pentyl phosphine oxide (CGI® 403 available from Ciba Corporation - 1 gram;
4. 2,2'-(1,2-Ethanediyldi-4,1-phenylene)bisbenzoxazole, Eastobrite® OB-1 Fluorescent Brightener (available from Eastman Chemical Company) - 1 gram;
5. Methyl Ethyl Ketone - 88 grams.

After exposure and development the material gave a solid step 11.

Example 9

Example 8 was repeated, except the photosensitive solution was coated on grained and anodized aluminum surface, giving a planographic printing plate.

After exposure and development the printing plate gave a solid step 13.

Claims

1. A photopolymerizable composition which comprises

- A) one or more ethylenically unsaturated, free-radical polymerizable monomers;
- B) one or more organic binders; and
- C) one or more photoinitiators, wherein the photoinitiator is an acyl or diacyl phosphine oxide, in combination with a fluorescent optical brightener.

2. The composition of claim 1 comprising from about 20 weight percent to about 50 weight percent of the one or more ethylenically unsaturated, free-radical polymerizable monomers; from about 40 weight percent to about 70 weight percent of the one or more organic binders; and from about 5 weight percent to about 15 weight percent of the one or more photoinitiators.

3. The composition of claim 2 comprising from about 10 weight percent to about 60 weight percent of the one or more ethylenically unsaturated, free-radical polymerizable monomers.

4. The composition of claim 2 comprising from about 5 weight percent to about 70 weight percent of the one or more ethylenically unsaturated, free-radical polymerizable monomers.

5. The composition of claim 2 comprising from about 20 weight percent to about 80 weight percent of the one or more organic binders.

6. The composition of claim 2 comprising from about 30 weight percent to about 70 weight percent of the one or more organic binders.


7. The composition of claim 2 comprising from about 3 weight percent to about 20 weight percent of the one or more photoinitiators.

8. The composition of claim 2 comprising from about 1 weight percent to about 30 weight percent of the one or more photoinitiators.


9. The composition of claim 1 wherein the one or more ethylenically unsaturated, free-radical polymerizable monomers is an acrylate or methacrylate.

10. The composition of claim 1 wherein the one or more organic binders is selected from the group consisting of styrene/maleic anhydride copolymers and their half esters; acrylic polymers and copolymers; polyamides; polyvinyl pyrrolidones; cellulosic resins; phenolic resins; polyvinyl acetals; polyvinyl acetates and their copolymers; and mixtures thereof.

11. The composition of claim 1 wherein the acyl and diacyl phosphine oxide have the following formulas:



Formula I



Formula II

where:

R₁ and R₆ is a branched or unbranched alkyl of 1 to 18 carbon atoms, substituted or unsubstituted cycloalkyl of 5 or 6 carbon atoms, C₆-C₁₈ aryl which is unsubstituted or substituted by a C₁-C₁₈ alkyl or C₁-C₁₈ alkoxy, or an S-containing or N-containing five-membered or six-membered heterocyclic radical, R₁ and R₆ being the same or different,

R₂ has the same meaning as R₁, or is C₁-C₁₈ alkoxy, C₆-C₁₈ aryloxy or aralkoxy (C₆-C₁₈ aryl, C₁-C₁₈ alkyl), R₁ and R₂ being the same or different or together to form a ring, and

R₃, R₄ and R₅ are a tertiary alkyl of 4 to 18 carbon atoms, or a tertiary cycloalkyl of 5 or 6 carbon atoms, or is a C₆-C₁₈ cycloalkyl, C₆-C₁₈ aryl, or 5-membered or 6-membered heterocyclic radical containing S, N or O as heteroatoms which contain substituents A and B bonded at least to the two ring carbon atoms, capable of sub-

stitution, which are adjacent to the point of attachment to the carbonyl group of the R₃ group, A and B being identical or different, and each being C₁-C₁₈ alkyl, C₁-C₁₈ alkoxy, C₁-C₁₈ alkoxy, C₁-C₁₈ alkyl, C₁-C₁₈ alkylthio, C₆-C₁₈ cycloalkyl, C₆-C₁₈ aryl or halogen R₃, R₄ and R₅ can be the same or different.

14. The composition of claim 1 wherein the fluorescent optical brightener is selected from the group consisting of 2,2'-(thiophenediyl)-bis-(t-butyl benzoxazole); 2-(stibyl-4'')-(naphtho-1',2',4,5)-1,2,3-triazole-2''-sulfonic acid phenyl ester; and 7-(4'-chloro-6''-diethylamino-1',3',5'-triazine-4'-yl)amino-3-phenyl coumarin.

15. The composition of claim 1 wherein the fluorescent optical brightener is selected from the group consisting of compounds whose building blocks include one or more of stilbene, triazine, thiazole, benzoxazole, coumarin, xanthene, triazole, oxazole, thiophene or pyrazoline.

16. A process for producing a photopolymerizable composition by providing an admixture of:

- A) one or more ethylenically unsaturated, free-radical polymerizable monomers;
- B) one or more organic binders; and
- C) a combination of an acyl or diacyl phosphine oxide compound and a fluorescent optical brightener.

17. The process of claim 16 comprising from about 20 weight percent to about 50 weight percent of the one or more ethylenically unsaturated, free-radical polymerizable monomers; from about 40 weight percent to about 70 weight percent of the one or more organic binders; and from about 5 weight percent to about 15 weight percent of the one or more photoinitiators.

18. The process of claim 17 comprising from about 10 weight percent to about 60 weight percent of the one or more ethylenically unsaturated, free-radical polymerizable monomers.

19. The process of claim 17 comprising from about 5 weight percent to about 70 weight percent of the one or more ethylenically unsaturated, free-radical polymerizable monomers.

20. The process of claim 17 comprising from about 20 weight percent to about 80 weight percent of the one or more organic binders.

21. The process of claim 17 comprising from about 30 weight percent to about 70 weight percent of the one or more organic binders.


22. The process of claim 17 comprising from about 3 weight percent to about 20 weight percent of the one or more photoinitiators.

23. The process of claim 17 comprising from about 1 weight percent to about 30 weight percent of the one or more photoinitiators.


24. The process of claim 16 wherein the one or more ethylenically unsaturated free-radical polymerizable monomers is an acrylate or methacrylate.

25. The process of claim 16 wherein the one or more organic binders is selected from the group consisting of styrene/maleic anhydride copolymers and their half esters; acrylic polymers and copolymers; polyamides; polyvinyl pyrrolidones; cellulosic resins; phenolic resins; polyvinyl acetals; polyvinyl acetates and their copolymers; and mixtures thereof.

26. The process of claim 16 wherein the acyl and diacyl phosphine oxide has the following formulas:



Formula I



Formula II

where:

R₁ and R₆ is a branched or unbranched alkyl of 1 to 18 carbon atoms, substituted or unsubstituted cycloalkyl of 5 or 6 carbon atoms, C₆-C₁₈ aryl which is unsubstituted or substituted by C₁-C₁₈ alkyl or C₁-C₁₈ alkoxy, or an S-containing or N-containing five-membered or six-membered heterocyclic radical, R₁ and R₆ being the same or different,

R₂ has the same meaning as R₁, or is C₁-C₁₈ alkoxy, C₆-C₁₈ aryloxy or aralkoxy (C₆-C₁₈ aryl, C₁-C₁₈ alkyl), R₁ and R₂ being the same or different or together to form a ring, and

R₃, R₄ and R₅ are a tertiary alkyl of 4 to 18 carbon atoms, or a tertiary cycloalkyl of 5 or 6 carbon atoms, or is a C₆-C₁₈ cycloalkyl, C₆-C₁₈ aryl, or 5-membered or 6-membered heterocyclic radical containing S, N or O as heteroatoms which contain substituents A and B bonded at least to the two ring carbon atoms, capable of substitution, which are adjacent to the point of attachment to the carbonyl group of the R₃ group, A and B being identical or different, and each being C₁-C₁₈ alkyl, C₁-C₁₈ alkoxy, C₁-C₁₈ alkoxy, C₁-C₁₈ alkyl, C₁-C₁₈ alkylthio, C₆-C₁₈ cycloalkyl, C₆-C₁₈ aryl or halogen. R₃, R₄ and R₅ can be the same or different.

27. The process of claim 16 wherein the fluorescent optical brightener is selected from the group consisting of 2,2'-(thiophenediyl)-bis-(t-butyl benzoxazole); 2-(stilbyl-4'')-(naphtho 1',2',4,5)-1,2,3-triazole-2''-sulfonic acid phenyl ester; and 7-(4'-chloro-6''-diethylamino-1',3',5'-triazine-4'-yl)amino-3-phenyl coumarin.

28. The process of claim 16 wherein the fluorescent optical brightener is selected from the group consisting of compounds whose building blocks include one or more of stilbene, triazine, thiazole, benzoxazole, coumarin, xanthene, triazole, oxazole, thiophene or pyrazoline.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 20 1158

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP-A-0 412 495 (E.I. DU PONT DE NEMOURS AND COMPANY) 13 February 1991 * page 11; table 1 * * page 7, line 48 - line 54 * ---	1-28	G03F7/029 G03F3/10
A	EP-A-0 446 175 (CIBA-GEIGY AG) 11 September 1991 * page 7; claims; example 1 * ---	1-28	
A	EP-A-0 298 030 (CIBA-GEIGY AG) 4 January 1989 * column 14; example 9 * * column 15; example 13 * ---	1-28	
A,D	US-A-5 300 399 (HOECHST CELANESE CORPORATION) 5 April 1994 * column 6, line 40 - line 44 * -----	1-28	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			G03F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27 August 1996	Examiner J.-M. DUPART
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1503 03.82 (P04 C01)